

Test Report No. <u>9875/17</u> Sassuolo, 21/03/18

Requested by:	uested by: GAMBINI GROUP S.p.A. Via Radici in Piano, 675 – 41049 SASSUOLO (MO)					
For the sample: Glazed ceramic tiles 35,5 x 71 x 0,9 cm marked "Articolo MARMI CARRARA BIANCO 35,5x71 cm".						
On (date): 27/12/17		Date of receipt in laboratory (sample delivered by the client): 12/12/17				
Test date		From: 11/01/18	To: 11/01/18			

EN 101 - Determination of scratch hardness of surface according to Mohs

Test specimens	1	2	3
Mohs hardness	5	5	5

Eng. Giordana Carani Technical approval

Prof. Maria Chiara Bignozzi

Director