

Requested by:	GAMBINI GROUP S.p.A. Via Radici in Piano, 675 – 41049 SASSUOLO (MO)		
For the sample:	Glazed ceramic tiles 35,5 x 71 x 0,9 cm marked "Articolo MARMI LATINA CREMA 35,5x71 cm".		
On (date):	27/12/17	Date of receipt in laboratory (sample delivered by the client): 12/12/17	
Test date	From: 11/01/18		To: 15/01/18

**EN ISO 10545 – 13 - Determination of chemical resistance**

Procedure followed: contact on proper surface  partial immersion

Test solutions		Classification		
		Test specimen 1	Test specimen 2	Test specimen 3
<b>Household chemicals</b>	Ammonium Chloride 100g/l	A(V)	A(V)	A(V)
<b>Swimming pool salts</b>	Sodium hypochlorite 20mg/l	A(V)	A(V)	A(V)
<b>Acids</b>	Hydrochloric acid 3% V/V	LA(V)	LA(V)	LA(V)
	Citric acid 100g/l	LA(V)	LA(V)	LA(V)
<b>Alkalis</b>	Potassium Hydroxide 30g/l	LA(V)	LA(V)	LA(V)
<b>Acids</b>	Hydrochloric acid 18%V/V	HA(V)	HA(V)	HA(V)
	Lactic acid 5% V/V	HA(V)	HA(V)	HA(V)
<b>Alkalis</b>	Potassium Hydroxide 100g/l	HA(V)	HA(V)	HA(V)

Pencil test applies:  yes  Reflexion test applies:  not

**Legenda**

**L:** low concentrations solutions  
**H:** high concentrations solutions  
**V:** visual classification (when pencil test and/or reflexion test **are not** applicable)

Classe **A:** no visible effect  
Classe **B:** discernable visible change in appearance  
Classe **C:** partial or complete loss of the original surface appearance

Eng. Giordana Carani  
Technical approval



Prof. Maria Chiara Bignozzi  
Director



The results reported relate only to the samples tested. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction. This test report consists of 1 pages, this cover included.