

Requested by:	GAMBINI GROUP S.p.A. Via Radici in Piano, 675 – 41049 SASSUOLO (MO)	
For the sample:	Glazed ceramic tiles 35,5 x 71 x 0,9 cm marked "Articolo MARMI LATINA CREMA 35,5x71 cm".	
On (date):	27/12/17	Date of receipt in laboratory (sample delivered by the client): 12/12/17
Test date	From: 11/01/18	To: 11/01/18

DIN 51097 (11/1992) – Determination of anti – slip properties.
Wet-loaded barefoot areas – Walking method – Ramp test


WORKING CONDITIONS:

Size of the tested surface (m):	0,50 x 1,20
Joint width (mm):	2
Grout:	Cement mortar
Surface orientation:	None

RESULTS

Average slip angle:	12,1°
Application range:	A

Eng. Giordana Carani
Technical approval



Prof. Maria Chiara Bignozzi
Director



The results reported relate only to the samples tested. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction. This test report consists of 1 pages, this cover included.