

Requested by:	GAMBINI GROUP S.p.A. Via Radici in Piano, 675 – 41049 SASSUOLO (MO)		
For the sample:	Glazed ceramic tiles 35,5 x 71 x 0,9 cm marked "Articolo MARMI LATINA FUMO 35,5x71 cm".		
On (date): 27/12/17	Date of receipt in laboratory (sample delivered by the client): 12/12/17		
Test date	From: 17/01/18	To: 22/01/18	

EN ISO 10545-7 – Determination of resistance to surface abrasion – Glazed tiles

ABRASION STAGE:

PEI, failure visible at (rev.):

1500

Test solutions	Resistance class (ISO 10545-14)				
	Test specimen 1	Test specimen 2	Test specimen 3	Test specimen 4	Test specimen 5
Stains					
Chrome green in light oil	-----	-----	-----	-----	-----
Iodine (alcoholic solution 13g/l)	-----	-----	-----	-----	-----
Olive oil (def. Olive Oil Agreement - 1979)	-----	-----	-----	-----	-----

CLASSIFICATION:

Abrasion class:

3

Stain resistance class - References

Resistance class 1: Stain not removed.

Resistance class 2: Stain removed by dipping in a suitable solvent for 24 hours.

Resistance class 3: Stain removed by mechanical cleaning and strong cleansing agent.

Resistance class 4: Stain removed by manual cleaning with weak cleansing agent .

Resistance class 5: Stain removed by means of hot current water for 5 min.

Eng. Giordana Carani
Technical approval



Prof. Maria Chiara Bignozzi
Director



The results reported relate only to the samples tested. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction. This test report consists of 1 pages, this cover included.