













**CARATTERISTICHE TECNICHE / TECHNICAL FEATURES / CARACTERISTIQUES TECHNIQUES/  
TECHNISCHE EINGESCHAFTEN**

	CARATTERISTICHE TECNICHE TECHNICAL SPECIFICATION	NORMA REGULATION	VALORE PRESCRITTO DALLA NOR- MA EN 14411 ISP 13006 REQUIRED STANDARDS	MARMI
	RESISTENZA AL GELO FROST RESISTANCE	UNI EN ISO 10545-2 ASTM C1026	RESISTENTI RESISTANT	<b>INGELIVO</b>
	RESISTENZA ALL'ABRASIONE RESISTANCE TO ABRASION	UNI EN ISO 10545-7	PEI	<b>DA PEI 3 A PEI 5 A SECONDA DEI COLORI DEPENDING ON THE COLORS</b>
	RESISTENZA ALLO SCIVOLAMENTO SLIP RESISTANCE	DIN 51130	R	<b>IN R9</b>
	RESISTENZA ALL'ATTRITO STATICO STATIC COEFFICIENT OF FRICTION	ASTM C 1028	$U \geq 0,6$	Wet. 0,35 Dry 0,83
	COEFFICIENTE DI ATTRITO DINAMICO DYNAMIC COEFFICIENT OF FRICTION	ANSI A137-1:2012	$\geq 0,42$	<b>M &gt; 0,25</b>
	DUREZZA MOHS HARDNESS IN MOHS DEGREES	UNI EN 101-1992	MOHS	<b>5</b>
	RESISTENZA ALL'URTO IMPACT RESISTANCE	UNI EN ISO 10545-5	VALORE DICHIARATO DECLARED VALUE	<b>0,82</b>
	RESISTENZA ALLA FLESSIONE FLEXION RESISTANCE	UNI EN ISO 10545-4	$S \geq 700 \text{ N } (< 7,5 \text{ mm})$ $S \geq 1300 \text{ N } (> 7,5 \text{ mm})$ $R \geq 35 \text{ N/mm}^2$	<b>44 N/mm2</b>
	ASSORBIMENTO D'ACQUA WATER ABSORPTION	UNI EN ISO 10545-3	$\leq 0,5 \%$	<b>0,25 %</b>
	RESISTENZA ALLE MACCHIE RESISTANT TO STAINING	UNI EN ISO 10545-14	SMALTATI $\geq 3$	<b>4-5</b>
	RESISTENZA CHIMICA CHEMICAL RESISTANCE	UNI EN ISO 10545-13	$\leq \text{GB}$	<b>A-LA-HA</b>
	RESISTENZA AGLI SBALZI TERMICI RESISTANCE TO THERMAL SHOCKS	UNI EN ISO 10545-9	RESISTENTI RESISTANT	<b>RESIST.</b>