

## TECHNICAL FEATURES

|  |
|--|
| MODEL: <b>WHITE CALACATA 1.</b>  |
| SIZE: <b>60x60</b>   |
| THICKNESS(mm): <b>9.5</b>  |
| DATE: <b>19/07/2023</b>  |
| CODE: <b>004.840.0001.12261</b>  |
| GROUP: <b>GROUP B1a UNE-EN 14411 Annex G / SASO ISO 13006:2018 Annex G</b> |
| TILE TYPE: <b>GL</b>   |
| FINISH: <b>LEVIGLASS</b>   |
| FAMILY: <b>LEVIGLASS-POLISHED GLAZED RECTIFIED PORCELAIN TILES</b>         |
| NUMBER OF DESIGNS:   |



| TEST   | RESULT  |                                   |
|--|---|-----------------------------------|
| <b>UNE-EN ISO 10545-2</b> DIMENSIONAL FEATURES                   | <b>COMPLIES WITH THE STANDARD</b>                 |                                   |
| <b>UNE-EN ISO 10545-3</b> WATER ABSORPTION                       | <b>&lt;= 0,5 %</b>                                |                                   |
| <b>UNE-EN ISO 10545-4</b> MODULUS OF RUPTURE - BREAKING STRENGTH | <b>1600-2400 N</b>                                |                                   |
|  | MODULUS OF RUPTURE - BENDING STRENGTH             | <b>35-45 N/mm2</b>                |
| <b>UNE-EN ISO 10545-6</b> RESISTANCE TO DEEP ABRASION (MM3)      | <b>NOT APPLY</b>                                  |                                   |
| <b>UNE-EN ISO 10545-7</b> RESISTANCE TO SURFACE ABRASION         | <b>-</b>  |                                   |
| <b>UNE-EN ISO 10545-8</b> LINEAR THERMAL EXPANSION               | <b>&lt;7,0 x 10-6 °C-1</b>                        |                                   |
| <b>UNE-EN ISO 10545-9</b> THERMAL SHOCK RESISTANCE               | <b>RESISTS</b>                                    |                                   |
| <b>UNE-EN ISO 10545-11</b> CRAZING RESISTANCE                    | <b>RESISTS</b>                                    |                                   |
| <b>UNE-EN ISO 10545-12</b> FROST RESISTANCE                      | <b>RESISTS</b>                                    |                                   |
| <b>UNE-EN ISO 10545-13</b>                                       | CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L   | <b>A</b>                          |
|  | CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L | <b>A</b>                          |
|  | CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3%        | <b>COMPLIES WITH THE STANDARD</b> |
|  | CHEMICAL RESISTANCE - CITRIC ACID 100 G/L         | <b>COMPLIES WITH THE STANDARD</b> |
|  | CHEMICAL RESISTANCE - POTASSIUM HYDROXYDE 30 G/L  | <b>COMPLIES WITH THE STANDARD</b> |
| <b>UNE-EN ISO 10545-14</b>                                       | STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL       | <b>5</b>                          |
|  | STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL     | <b>5</b>                          |
|  | STAIN RESISTANCE - OLIVE OIL                      | <b>5</b>                          |

SLIP RESISTANCE

|  | TEST              |  | RESULT |
|--|-------------------|--|--------|
|  | UNE 41901:2017 EX | SLIP RESISTANCE (PENDULUM)                                 | -      |
|  | DIN 51130         | CRITICAL ANGLE OF SLIP (INCLINED PLATFORM)                 | -      |
|  | DIN 51097         | CRITICAL ANGLE OF SLIP. WET-LOADED BAREFOOT AREAS          | -      |
|  | BS7976 (PTV) WET  | CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) WET | -      |
|  | ANSI A326.3       | DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF RIGID FLOORS.    | -      |

| TEST        |                    | VALOR UPEC |
|-------------|--------------------|------------|
| <u>UPEC</u> | UPEC CERTIFICATION | -          |

Declaration of Performance:

[https://www.pamesa.com/ERP/4.0/empresas/151/045/ficheros/t00030006/113/DdP\\_DoP\\_N003CPR2013.pdf](https://www.pamesa.com/ERP/4.0/empresas/151/045/ficheros/t00030006/113/DdP_DoP_N003CPR2013.pdf)

TECHNICAL DEPARTMENT  
PAMESA CERÁMICA